

# Nexseal™ 2.0

## Spray Foam Insulation

### Division 7: Thermal & Moisture Protection



#### Product Description:

Nexseal™ 2.0 spray foam insulation is a spray-applied, two component, closed cell polyurethane foam insulation system compliant with ASTM C-1029 Type II foams. The product is formed by the reaction of proprietary resin blend and polymeric methylene diphenyl diisocyanate. The resin blend is comprised of Polyols, additives, fire retardants and Solstice LBA by Honeywell, which is based on hydrofluoroolefin (HFO) technology.

The spray applied nature of Nexseal™ 2.0 spray foam allows the material to flow into voids and seal cracks, expanding to form a monolithic structure with high R-value (resistance to heat flow). Nexseal™ 2.0 spray foam can form various control layers for buildings and structures: insulation, air barrier, moisture retarder and weather barrier.

#### Product Uses:

Cold Storage	Walls	Attics
Crawlspaces	Tanks	Pipe Insulation
Exterior Applications	Ducts	Foundations
Concrete Slab		

#### Typical Physical Attributes:

Property <sup>†</sup>	Test Method	Value
Apparent Density	ASTM D-1622	2 lbs/ft <sup>3</sup> (nominal)
R-value (aged)	ASTM C-518	7.2 R/in
Compressive Strength	ASTM D-1621	nom. 25 lbs/in <sup>2</sup>
Tensile Strength	ASTM D-1623	nom. 50 lbs/in <sup>2</sup>
Closed Cell Content	ASTM D-6226	> 90% (vol.)
Water Absorption	ASTM D-2842	< 2%
Water Vapor Permeance	ASTM E-96	< 2 perm-inches
Fungi Resistance	ASTM C-1338	No growth
Flame Spread Index	ASTM E-84	< 25
Smoke Developed Index	ASTM E-84	< 450
Dimensional Stability, -20°F	ASTM D-2126	< 5% Change
Dimensional Stability, +200°F	ASTM D-2126	< 10% Change
Dimensional Stability, +158°F & 100%RH	ASTM D-2126	< 10% Change
Ignition Barrier	ICC ES AC377 Appendix X	Pass no coating
Thermal Barrier	NFPA 286	Pass DC315 89 ft <sup>2</sup> /gal
Global Warming Potential	n/a	1

<sup>†</sup> These values are typical. However values will vary and should not be considered part of the product specifications. It is imperative that the trained applicator read and understand this technical datasheet and SDS to process the material correctly and understand environmental and equipment limitations.

#### ASTM E-84:

Nexseal™ 2.0 spray foam is an ASTM E-84 (NFPA 255, UL723) class 1 (Class A) spray foam insulation.

Flame Spread Index <25

Smoke Developed Index <450

Thickness 4 inches

*These numerical flame spread values are not a true reflection on how this or any material will perform in actual fire conditions.*

#### Thermal Barriers:

Nexseal™ 2.0 spray foam must be separated from the interior of the building (occupied space) by an approved 15 minute thermal barrier such as ½" inch gypsum board or other equivalent material. Consult local building codes for requirements and restrictions.

#### Chemical Attributes:

Component	Viscosity (25°C)	Density
Isocyanate	200 cps	10.3 lbs/gal
Resin	700 cps	10.3 lbs/gal

**Storage & Shelf Life:**

Nexseal™ 2.0 spray foam components have an optimal shelf life of 6 months when stored in unopened containers at temperature between 50 – 70°F. Excessively high temperatures may reduce optimal shelf life. Store material at 70 – 90°F for 48 hours prior to application of the product.

**Environmental Considerations:**

Nexseal™ 2.0 spray foam insulation is available in two grades for various environmental conditions:

**AMBIENT & SUBSTRATE****TEMPERATURE**

Regular	Winter
50 - 110°F	30 - 80°F

Wind speeds in excess of 10 mph may cause loss of exotherm or cause overspray onto adjacent objects or structures. It may be necessary to use wind screens.

**Substrate Preparation:**

All surfaces must be clean and dry, free of dirt, oil, solvents, grease and loose particles for optimal adhesion. Nexseal™ 2.0 spray foam bonds tenaciously to most clean substrates. Moisture content of wood products should be < 18% and concrete must age at least 28 days before application of Nexseal™ 2.0 spray foam can occur. Consult SES Foam for specific recommendations on primers or substrates.

**Service Temperature:**

Nexseal™ 2.0 spray foam insulation is designed to be used in ambient temperatures from -40°F and 180°F, 220°F intermittent. It is strongly recommended that test sprays be conducted before installation for use in extreme temperatures.

**SPF Processing Parameters:**

Nexseal™ 2.0 spray foam is designed to be applied by trained contractors using high pressure, plural component spray proportioners. The spray proportioner must be able to maintain the designed temperature and pressure for Nexseal™ 2.0 spray foam products:

A/B/Hose Temperature	120 - 140°F
A/B Dynamic Pressure	1000 - 1500 lbs/in <sup>2</sup>

Optimal spray settings will vary with proportioner, hose dimensions, gun configuration and ambient conditions. It is critical for sprayers to understand the limitations associated with their equipment.

**Pass thickness:**

Nexseal™ 2.0 spray foam should be applied at a minimum thickness of ½ inch and a maximum thickness of 4 inches. If greater than 2 inch thickness is desired, sprayers should wait a minimum of 10 minutes between passes. For substrates with sensitivity to heat like plastic or metal, tests should be done to understand the effect of the SPF exotherm on the material. In some cases putting on a flash coat first is recommended to prevent any adverse effects on the substrates.

**Safety and Handling Information:**

It is critical to read and become familiar with the Safety Datasheets prior to working with Nexseal™ 2.0 spray foam liquid components. During application respiratory protection is required for the applicator and bystanders or helpers. For more information consult Safety Datasheets, [www.sesfoam.com](http://www.sesfoam.com), or [www.spraypolyurethane.org](http://www.spraypolyurethane.org)

The descriptions, data, designs and information contained herein are presented in good faith and believed to be accurate. This information is provided for guidance ONLY. Many factors will affect the processing or application of SES Foam LLC products, it is necessary that you make tests to determine ultimate suitability for SES Foam LLC products for your particular application. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described, data or designs presented. In no case shall the descriptions, information, data or designs provided be considered a part of our terms and conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. You expressly agree to release SES Foam LLC from all liability in tort or contract based on the technical information provided. All such information is accepted at your own risk.